Technical Data sheet

Nippopoxy 760 ZR

Product Description

Nippopoxy 760 ZR Primer is a two-pack, fast dry, zinc-rich epoxy primer. It is recommended where high level of corrosion resistance is required. It gives excellent corrosion resistance properties and ability to perform against the severe chemical environment.

Recommended Use

It is designed as a primer for long-life protection on steel surfaces of petrochemicals plant, power generations, offshore facilities, port machineries and hydro facilities in highly corrosion environment.

Physical Properties

Composition : Epoxy Resin cured with polyamide and pigmented with zinc dust

Volume Solids	: 60 ± 2%	**Temperature Resistance :**	
Mixing Ratio: Base: catalyst	: 3:1 (ByV/V)	Continuous	: 120^0 C
Pot Life:	: Min. 6 Hours	Intermittent	: 150^0 C
Application	: Flow/Airless spray/Convetinal spray	**Weatherability**	: Excellent with proper system
Recommended DFT	: 60-75 µ's per coat	**Flexibility**	: Moderate
Recommended WFT	: 100-125 µ's per coat	**Abrasion Resistance**	: Excellent
Theoretical Spreading Rate	: 8 - 10 m^2/ ltr	**Colour**	: Grey
Drying Time :		**Finish**	: Matt
Surface Dry	: Max. 60 min @ 30^0C	**Packing** .	: 20 Ltrs
Tack Free	: Max. 90 minutes@30^0C	**Thinner**	: Thinner 1501
Hard dry	: 6-7 Hours@30^0C	**Chemic resistanace:**	
Overcoating Interval :		**Acid & Alkali**	Very good with proper System
MIN.	: 6 Hours	**Oil resistance**	Very good with proper System
MAX.	: 15 days	**Solvent Resistance**	Very good with proper System

Storage Life : Upto 12 months when kept under sealed and controlled condition.

Surface Preparation

Steel: Remove grease, oil and other contaminants preferably by Solvent Cleaning to SP 1. Abrasive blast clean to a minimum of SSPC SP10/Sa2.5. For severe corrosive conditions, blast to SSPC SP 5 with a surface profile not exceeding 35-52 microns. If blasting is not practical, make full use of mechanical tools along with manual chipping and wire brushing to remove loose rust and scale to SSPC SP 2 / SP3. Excessive burnishing of steel is to be avoided. Thoroughly dust down all surfaces. The surface should be clean and dry before application of primer.Hydro-blasting for maintenance structures is preferred choice where there are heavy deposits of contaminants. Ultra-high pressure hydro-blasting equivalent with light flash rusting as per standards NACE NO. 5 or SSPC SP 12- WJ2 and NV2 as referred in SSPC vis-5 pictorial standard.

Appliaction Details

Stir the component A and B separately and then mix the base and Hardener as per the recommended mixing ratio. Mix the paint properly after the addition of base and Hardener and allow it to mature for 10-15 minutes and stir again before use and during application. For **conventional Spray** Add thinner 1501 20-40% to get a proper application pattern. **Brush:** Apply preferably without thinning. However, if required during application, add up to 5% Thinner 1501. Brushing is recommended for stripe coat and touch-up of critical areas.

Technical Data sheet

Nippopoxy 760 ZR

For Airless Spray : Tip Size : 0.017" – 0.031"
Pressure at Nozzle : 180 – 200 kg/cm2
Thinner Intake: 5-15%

Recommended system:

Intermediate Coat:

1. Nippopoxy 680 HS MIO
2. Nippopoxy 675F MIO
3. Nippopoxy 692 HS HB Mastic
4. Indopoxy 645 MIO

Finish Coat:

1. Nippothane 1070
2. Nippothane 1066HS
3. Nippothane 2075G

Precautions

1. Do not apply in rain, fog or mist and when the surface temperature is 50^0C and above.
2. Material should be used under speculate pot life.
3. The spray machine hose and paint storage equipement should clean with thinner 1501 to avoid blockage and damage.
4. Below 10^0 C and above 85% Relative humidity appliaction should be avoided. It creates paint defect.
5. application should be avoided when substrate temperature is less than 3^0C than the dew point temperature

Disclaimer

The information in this data sheet is given to the best of Nippon Paint's (Indokote Industries Pvt. Ltd. is 100% subsudary of Nippon Paint India Pvt. Ltd.) knowledge and practical experience. Users may consult with Nippon Paint on the general suitability of the product for their needs and specific application practices though it remains each user's responsibility to determine the suitability of the product for the user's particular use. The condition of the substrate and application are not within Nippon Paint's control. Therefore no implied conditions, warranties or other terms will apply to the Product. Nippon Indokote Paint does not and cannot warrant the results which the user may obtain by using the product. In no event will Nippon Paint be liable to the user for any kind of loss (whether direct or indirect) even if Nippon Paint was previously advised of it. In line with Nippon Paint's policy for continuous development, Nippon Paint reserves the right to modify the product and the information in this data sheet without prior notice. It is the user's responsibility to check with Nippon Paint for the latest version of this data sheet. Thisdata sheet has been translated into various languages. In the event of any inconsistency, the English version shall prevail

TDS No. 2024/01
Version: 00

NIPPON PAINT INDOKOTE INDUSTRIES PVT. LTD.
PLOT NO. 160, SECTOR 3, HSIDC GROWTH CENTRE, IMT BAWAL, HARYANA 123501
Phone : +91-9015400200
Help Desk: catalyst@nipponpaint.co.in, web site: www.nipponpaint.co.in