Technical Data sheet

Indopoxy 320 SG

Product Description

Indopoxy 320 SG is a Two component amine cured fast drying anti corrosive general industrial primer containing Zinc Phosphate as corrosion inhibiting pigments.

Recommended Use

It is recommended as undercoat on M.S. and concrete surface in diverse areas of use in Industries and maintenance projects. Indopoxy 320 SG is recommended for General & Heavy Fabrication industries, OEM components, Chemical and Pharmaceutical Industries, MS structures, PEBs due to its fast drying and abrasion resistance qualities. It can be overcoated within one hour of application at ambient temperature, hence making it ideal to be use in variety of applications.

Physical Properties

Composition : Epoxy Resin cured with polyamide.

Volume Solids	: 45 ± 2%	**Temperature Resistance :**	
Mixing Ratio: Base: catalys	: 4:1 (ByV/V)	Continuous	: 100^0 C
Pot Life:	: 3 Hours	Intermittent	: 120^0 C
Application	: Airless spray/Convetinal spray		
Recommended DFT	: 40-60 µ's per coat	**Flexibility**	: Good
Recommended WFT	: 88.8 - 133.3 µ's per coat	**Abrasion Resistance**	: Very good
Theoretical Spreading Rate	: 7.5 - 11.25 m^2/ ltr	**Colour**	: Grey
Drying Time :		**Finish**	: semi glossy
Surface Dry	: Max. 25 min @ 30^0C	**Packing** .	: 25 Ltrs combi
Tack Free	: Max. 3 Hour@30^0C	**Thinner**	: Thinner IK-1501
Hard dry	: 10 - 12 Hours@30^0C	**Chemic resistanace:**	
Overcoating Interval :		**Acid & Alkali**	: Very good with Topcoat
MIN.	: 10 Hours	**Oil resistance**	: Very good with Topcoat
		Solvent	
MAX.	: 30 days	**Resistance**	: Very good with Topcoat

Storage Life : Upto 12 months when kept under sealed and controlled condition.

Surface Preparation

All surfaces should be clean, dry, and free from contamination. The surface should be assessed and treated per ISO 8504. Oil or grease should be removed per SSPC-SP1 solvent cleaning. Damaged Area The Damaged area should be prepared with abrasive blast cleaning to Sa 2.5 (ISO 8501-1:2007). When abrasive blasting is impossible, mechanical cleaning St 3 (ISO 8501-1:2007) is acceptable.

Appliaction Details

Stir components A and B separately and then mix the base and Hardener as per the recommended mixing ratio. Mix the paint properly after mixing and allow it to mature for 10-15 minutes and stir again before use and during application. For conventional Spray Add thinner 1501 20-30% to get a proper application pattern. Brush: Apply preferably without thinning. However, if required during the application, add up to 5% Thinner 1501. Brushing is recommended for stripe coat and touch-up of critical areas.

Technical Data sheet

Indopoxy 320 SG

For Airless Spray : Tip Size : 0.017” – 0.027”
Pressure at Nozzle : 180 – 200 kg/cm2
Thinner Intake: 0-10%

Recommended system:

Top Coat:

1. Indothane 4080
2. Indothane 1070 / 1067HS
3. Valuthane PU
4. Indothane 4090X

Precautions

1. Do not apply in rain, fog or mist and when the surface temperature is 50^0C and above.
2. Material should be used under speculate pot life.
3. The spray machine hose and paint storage equipement should clean with thinner 1702 or 1501 to avoid blockage and damage.
4. Below 10^0 C and above 85% Relative humidity appliaction should be avoided. It creates paint defect.
5. application should be avoided when substrate temperature is less than 3^0C than the dew point temperature

Disclaimer

The information in this data sheet is given to the best of Nippon Paint’s (Indokote Industries Pvt. Ltd. is 100% subsudary of Nippon Paint India Pvt. Ltd.) knowledge and practical experience. Users may consult with Nippon Paint on the general suitability of the product for their needs and specific application practices though it remains each user’s responsibility to determine the suitability of the product for the user’s particular use. The condition of the substrate and application are not within Nippon Paint’s control. Therefore no implied conditions, warranties or other terms will apply to the Product. Nippon Indokote Paint does not and cannot warrant the results which the user may obtain by using the product. In no event will Nippon Paint be liable to the user for any kind of loss (whether direct or indirect) even if Nippon Paint was previously advised of it. In line with Nippon Paint’s policy for continuous development, Nippon Paint reserves the right to modify the product and the information in this data sheet without prior notice. It is the user’s responsibility to check with Nippon Paint for the latest version of this data sheet. Thisdata sheet has been translated into various languages. In the event of any inconsistency, the English version shall prevail

TDS No. 2024/01
Version: 00

NIPPON PAINT INDOKOTE INDUSTRIES PVT. LTD.
PLOT NO. 160, SECTOR 3, HSIDC GROWTH CENTRE, IMT BAWAL, HARYANA 123501
Phone : +91-9015400200
Help Desk: catalyst@nipponpaint.co.in, web site: www.nipponpaint.co.in